


Steel Pipe


Code #	Description	Size
--------	-------------	------



SCH-40 Black Threaded & Coupled

Cont. Weld A120/A53F GR A; 21 Foot Lengths


1-0520	SCH-40 Black Threaded & Coupled	1/2"
1-0525	SCH-40 Black Threaded & Coupled	3/4"
1-0530	SCH-40 Black Threaded & Coupled	1"
1-0535	SCH-40 Black Threaded & Coupled	1-1/4"
1-0540	SCH-40 Black Threaded & Coupled	1-1/2"
1-0545	SCH-40 Black Threaded & Coupled	2"



SCH-40 Galvanized Threaded & Coupled

Cont. Weld A120/A53F GR A; 21 Foot Lengths


1-1120	SCH-40 Galvanized Threaded & Coupled	1/2"
1-1125	SCH-40 Galvanized Threaded & Coupled	3/4"
1-1130	SCH-40 Galvanized Threaded & Coupled	1"
1-1135	SCH-40 Galvanized Threaded & Coupled	1-1/4"
1-1140	SCH-40 Galvanized Threaded & Coupled	1-1/2"
1-1145	SCH-40 Galvanized Threaded & Coupled	2"



SCH-40 Black Plain End Beveled

Beveled Cont. Weld A120/A53F GR A; 21 Foot Lengths

1-1720	SCH-40 Black Plain End Beveled	1/2"
1-1725	SCH-40 Black Plain End Beveled	3/4"
1-1730	SCH-40 Black Plain End Beveled	1"
1-1735	SCH-40 Black Plain End Beveled	1-1/4"
1-1740	SCH-40 Black Plain End Beveled	1-1/2"
1-1745	SCH-40 Black Plain End Beveled	2"



SCH-80 Black Plain End Beveled

Cont. Weld A120/A53F GR A; 21 Foot Lengths

1-3020	SCH-80 Black Plain End Beveled	1/2"
1-3025	SCH-80 Black Plain End Beveled	3/4"
1-3030	SCH-80 Black Plain End Beveled	1"
1-3035	SCH-80 Black Plain End Beveled	1-1/4"
1-3040	SCH-80 Black Plain End Beveled	1-1/2"



CONTINUOUS WELD STANDARD AND LINE PIPE DATA

Size, Inches Nominal OD	Wall Thickness, Inches	Nominal Weight Lbs./Ft.				Class	Mill Test* Pressure psi	Calculated Internal Pressure at Min. Yield Strength psi		Calculated Ultimate Bursting Pressure+ psi		Size, Inches	
		Plain End	T & C		Class I O.H.			Class II O.H.	Class I O.H.	Class II O.H.	OD	Nom.	
			Standard Pipe Coupling	Line Pipe Coupling									
1/8	0.405	0.068	0.24	0.24	0.25	Std.	700	8400	9400	15120	16120	0.405	1/8
		0.095	0.31	-	0.32	XS	850	11730	13130	21120	22520		
1/4	0.540	0.088	0.42	0.42	0.43	Std.	700	8150	9130	14070	15050	0.540	1/4
		0.119	0.54	-	0.54	XS	850	11020	12330	19830	21150		
3/8	0.675	0.091	0.57	0.57	0.57	Std.	700	6730	7550	12130	12930	0.675	3/8
		0.126	0.74	-	0.74	XS	850	9330	10450	16800	17920		
1/2	0.840	0.109	0.85	0.85	0.86	Std.	700	6480	7270	11680	12450	0.840	1/2
		0.147	1.09	-	1.09	XS	850	8750	9800	15750	16800		
3/4	1.050	0.113	1.13	1.13	1.14	Std.	700	5380	6030	9680	10340	1.050	3/4
		0.154	1.47	-	1.48	XS	850	7330	8220	13200	14080		
		0.308	2.44	-	-	XXS	1000	-	-	-	-		
1	1.315	0.133	1.68	1.68	1.70	Std.	700	5050	5670	9100	9720	1.315	1
		0.179	2.17	-	2.18	XS	850	6800	7620	12250	13070		
		0.358	3.66	-	-	XXS	1000	-	-	-	-		
1-1/4	1.660	0.140	2.27	2.28	2.30	Std.	1000	4220	4720	7580	8100	1.660	1-1/4
		0.191	3.00	-	3.02	XS	1300	5750	6450	10350	11050		
		0.382	5.21	-	-	XXS	1400	-	-	-	-		
1-1/2	1.90	0.145	2.72	2.73	2.75	Std.	1000	3820	4270	6870	7330	1.900	1-1/2
		0.200	3.63	-	3.66	XS	1300	5270	5900	9470	10100		
		0.400	6.41	-	-	XXS	1400	-	-	-	-		
2	2.375	0.154	3.65	3.68	3.75	Std.	1000	3230	3630	5830	6230	2.375	2
		0.218	5.02	-	5.07	XS	1300	4580	5130	8270	8820		
2-1/2	2.875	0.203	5.79	5.82	5.90	Std.	1000	3533	3950	6350	6780	2.875	2-1/2
		0.276	7.66	-	7.73	XS	1300	4800	5380	8360	9220		
3	3.500	0.156	5.57	-	-	-	-	-	-	-	-	3.500	3
		0.188	6.63	-	-	-	1000	2680	3000	4830	5150		
		0.216	7.58	7.62	7.70	Std.	1000	3080	3450	5550	5920		
		0.300	10.25	-	10.3	XS	1300	4280	4800	7720	8230		
3-1/2	4.000	0.188	7.63	-	-	-	1200	2350	2630	4230	4520	4.000	3-1/2
		0.226	9.11	9.20	9.25	Std.	1200	2830	3170	5080	5420		
		0.318	12.51	-	12.63	XS	1700	3970	4450	7150	7630		
4	4.500	0.156	7.25	-	-	-	1000	1730	1940	3120	3330	4.500	4
		0.188	8.64	-	-	-	1200	2080	2330	3770	4020		
		0.219	10.00	-	-	-	1200	-	-	-	-		
		0.237	10.79	10.89	11.00	Std.	1200	2630	2950	4730	5050		
		0.337	14.98	-	15.17	XS	1700	3750	4200	6730	7180		

* Mill test pressures are standard USS test pressures which equal or exceed specification test procedures.
 + Calculated pressure values are calculated on basis of minimum yield strength, minimum ultimate strength and nominal dimensions specified by API and ASTM.
 Note: Inquire for further information on ASTM A589 covering water well pipe and WWP-404 & WW-P-406b covering continuous weld pipe to federal specifications.